
product information

KHS Innocoll KS 1765





adhesives for labeling

- / based on casein / protein
- for glass
- 🖌 for paper / stanniol
- 🧹 high intitial tack
- 🗸 good resistance to condensate water
- raw materials correspond to the FDA Directives 21 CFR 175.
 105.

*example illustration

product characteristics

The product is suitable for applying labels to normal - and lightly - coated glass surfaces, e.g. in the beverage-, foodstuffs- and pharmaceutical industries etc. The product has a good resistance to condensate water and has a good initial tack; can be easily removed in a automatic bottle washing machine under normal industrial conditions.

application notes

The temperature processing range is 24 - 32 °C, ideal at approx. 28 °C. Before a different adhesive is to be used on the machine, it must be carefully cleaned.

storage

The product can be stored in its original sealed container for at least 6 months at room temperature after date of production - but not below +4 °C.

characteristics	Innocoll KS 1765	
viscosity, dyn.	70.000 ± 15.000 mPas	
colour	beige-transparent	
pH value	7,9 ± 0,3	
density	1,02 ± 0,03 g/cm3	

cont	tainer	packing size	material number
33	kg	18	301244607470
1050	kg	1	301244607471
30	kg	18	301244607550

To the best of our knowledge and experience, the data / information we have provided is reliable but it does not amount to a statement of assured properties in the context of the latest regulations issued by the Federal Court of Justice. With regard to the many options available in terms of alternative applications and operating conditions the data / information can only be regarded as of a non-binding nature. In each separate case it is necessary for you to carry out your own trials before large-scale use although, of course, in that respect our application technology is available to you upon request.