
IKHS Innocoll NP 2070 S





^{*}example illustration

adhesives for labeling

- semi hydrogels
- for glass
- for paper labels
- good resistance to condensate water
- easily removable in washmachine
- raw materials correspond to the FDA Directives 21 CFR 175. 105.

product characteristics

The product is suitable for applying labels to normal - and lightly - coated glass surfaces, e.g. in the beverage-, foodstuffs- and pharmaceutical industries etc. The product has a good resistance to condensate water and can be easily removed in a automatic bottle washing machine under normal industrial conditions.

application notes

The temperature processing range is 27 - 33 °C. Before a different adhesive is to be used on the machine, it must be carefully cleaned.

storage


The product can be stored in its original sealed container for at least 6 months at room temperature after date of production - but not below +4 °C.

characteristics	Innocoll NP 2070 S
viscosity, dyn.	55.000 ± 15.000 mPas
colour	beige
open time	8,3 ± 0,2
softening Point (R&B)	$1,02 \pm 0,03 \text{ g/cm}3$

container	packing size	material number
33 kg	18	301244607280
1050 kg	1	301244607281
30 kg	18	301244607350

To the best of our knowledge and experience, the data / information we have provided is reliable but it does not amount to a statement of assured properties in the context of the latest regulations issued by the Federal Court of Justice. With regard to the many options available in terms of alternative applications and operating conditions the data / information can only be regarded as of a non-binding nature. In each separate case it is necessary for you to carry out your own trials before large-scale use although, of course, in that respect our application technology is available to you upon request.

KHS Innocoll NP 2070 S



To the best of our knowledge and experience, the data / information we have provided is reliable but it does not amount to a statement of assured properties in the context of the latest regulations issued by the Federal Court of Justice. With regard to the many options available in terms of alternative applications and operating conditions the data / information can only be regarded as of a non-binding nature. In each separate case it is necessary for you to carry out your own trials before large-scale use although, of course, in that respect our application technology is available to you upon request.